

CMA Testing
and Certification
Laboratories

廠商會檢定中心

TPE 1/2

TEST REPORT

Report No. : AG021404-001 Date : 2006 August 30

Application No. : LG219717

Applicant : VALUE CHAIN NETWORK (HONG KONG) LTD
RM 1602, GLOBAL TRADE CTR.,
15 WING KIN ROAD,
KWAI CHUNG, N.T.,
HONG KONG.

Sample Description : One (1) submitted sample stated to be PROFLEX TPE/TPR GE-S Series.
Article No. : GE55S, GE60S, GE65S, GE70S, GE75S, GE80S, GE85S,
GE90S ***

Date Received : 2006 August 18.

Test Period : 2006 August 19 – 2006 August 25.

Test Requested : For material : plastics or non-stick coating
– Overall migration test for compliance with 2002/72/EC Directive for plastic
materials and articles intended to come into contact with foodstuffs


Test Method : As specified in 82/711/EEC, 85/572/EEC and 97/48/EC Directives; with reference
to EN 1186 : Part 3 : 2002 (total immersion method, method A).

Test Result : Refer to the results on page 2.

Conclusion : The submitted sample was found to comply with the respective requirement(s) for
the tested item(s) as stated in the German Food & Feed Acts LFGB and Regulation
(EC) No. 1935/2004 (Material in contact with food regulation).

For and on behalf of
CMA Industrial Development Foundation Limited

Authorized Signature :


Wong Chuk Fung
Specialist - Chemical Division

Page 1 of 2



TEST REPORT

Report No. : AG021404-001

Date : 2006 August 30

Application No. : LG219717

Test Result :

Simulant Used	Test Condition (For repeated use)	Overall Migration (mg/dm ²)	Maximum Permissible Limit (mg/dm ²)
Distilled water	40°C for 24 hours	1.5	10

- Note :
1. mg/dm² denotes milligram per square decimetre
 2. °C denotes degree Celsius
 3. The specification was quoted from 2002/72/EC Directive.

***** End of Report *****